



Materials Data Sheets

Materials Simulating Engineering Plastics

Objet ABS-like Digital Material (RGD5160-DM) made of Objet RGD515 & Objet RGD535

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	55-60	psi	8000-8700
Elongation at break	D-638-05	MPa	25-40	psi	25-40
Modulus of elasticity	D-638-04	MPa	2600-3000	psi	375,000-435,000
Flexural Strength	D-790-03	MPa	65-75	psi	9,500-11,000
Flexural Modulus	D-790-04	MPa	1700-2200	psi	245,000-320,000
HDT, °C @ 0.45MPa	D-648-06	°C	58-68	°F	136-154
HDT, °C @ 0.45MPa after thermal post treatment procedure A	D-648-06	°C	82-90	°F	180-194
HDT, °C @ 0.45MPa after thermal post treatment procedure B	D-648-06	°C	92-95	°F	198-203
HDT, °C @ 1.82MPa	D-648-07	°C	51-55	°F	124-131
Izod Notched Impact	D-256-06	J/m	65-80	ft lb/inch	1.22-1.50
Tg	DMA, E ₉	°C	47-53	°F	117-127
Shore Hardness (D)	Scale D	Scale D	85-87	Scale D	85-87
Rockwell Hardness	Scale M	Scale M	67-69	Scale M	67-69

Objet High Temperature Material (RGD525)

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	70-80	psi	10,000-11,500
Elongation at break	D-638-05	%	10-15	%	10-15
Modulus of elasticity	D-638-04	MPa	3200-3500	psi	465,000-510,000
Flexural Strength	D-790-03	MPa	110-130	psi	16,000-19,000
Flexural Modulus	D-790-04	MPa	3100-3500	psi	450,000-510,000
HDT, °C @ 0.45MPa	D-648-06	°C	63-67	°F	145-163
HDT, °C @ 0.45MPa after thermal post treatment procedure A	D-648-06	°C	75-80	°F	167-176
HDT, °C @ 1.82MPa	D-648-07	°C	55-57	°F	131-135
Izod Notched Impact	D-256-06	J/m	14-16	ft lb/inch	0.262-0.300
Water Absorption, %	D-570-98 24hr	%	1.2-1.4	%	1.2-1.4
Tg	DMA, E ₉	°C	62-65	°F	144-149
Shore D	Scale D	Scale D	87-88	Scale D	87-88
Rockwell Hardness	Scale M	Scale M	78-83	Scale M	78-83
Polymerized density	ASTM D792	g/cm ³	0.97-0.98		
Ash content	USP281	%	0.38-0.42	%	0.38-0.42

Materials Simulating Standard Plastics

Transparent Materials

Objet FullCure720

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	50-65	psi	7250-9450
Elongation at break	D-638-05	%	15-25	%	15-25
Modulus of elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	80-110	psi	12000-16000
Flexural Modulus	D-790-04	MPa	2700-3300	psi	390,000-480,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.5-2.2	%	1.5-2.2
Tg	DMA, E ₉	°C	48-50	°F	118-122
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized density	ASTM D792	g/cm ³	1.18-1.19		
Ash content	USP281	%	0.01-0.02	%	0.01-0.02

Objet VeroClear FullCure810

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	50-65	psi	7250-9450
Elongation at break	D-638-05	%	10-25	%	10-25
Modulus of elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	75-110	psi	11000-16000
Flexural Modulus	D-790-04	MPa	2200-3200	psi	320,000-465,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.1-1.5	%	1.1-1.5
Tg	DMA, E ₉	°C	52-54	°F	126-129
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized density	ASTM D792	g/cm ³	1.04-1.05		
Ash content	USP281	%	0.02-0.06	%	0.02-0.06

Rigid Opaque Materials

Objet VeroGray FullCure850, VeroBlack FullCure870, VeroWhitePlus FullCure835

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	50-65	psi	7250-9450
Elongation at break	D-638-05	%	10-25	%	10-25
Modulus of elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	75-110	psi	11000-16000
Flexural Modulus	D-790-04	MPa	2200-3200	psi	320,000-465,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.1-1.5	%	1.1-1.5
Tg	DMA, E ₉	°C	52-54	°F	126-129
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized density	ASTM D792	g/cm ³	1.17-1.18		
Ash content VeroGray, VeroWhitePlus	USP281	%	0.23-0.26	%	0.23-0.26
Ash content VeriBlack	USP281	%	0.01-0.02	%	0.01-0.02

Objet VeroBlue FullCure840

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	50-60	psi	7250-8700
Elongation at break	D-638-05	%	15-25	%	15-25
Modulus of elasticity	D-638-04	MPa	2000-3000	psi	290,000-435,000
Flexural Strength	D-790-03	MPa	60-70	psi	8700-10200
Flexural Modulus	D-790-04	MPa	1900-2500	psi	265,000-365,000
HDT, °C @ 0.45MPa	D-648-06	°C	45-50	°F	113-122
HDT, °C @ 1.82MPa	D-648-07	°C	45-50	°F	113-122
Izod Notched Impact	D-256-06	J/m	20-30	ft lb/inch	0.375-0.562
Water Absorption	D-570-98 24hr	%	1.5-2.2	%	1.5-2.2
Tg	DMA, E ₉	°C	48-50	°F	118-122
Shore Hardness (D)	Scale D	Scale D	83-86	Scale D	83-86
Rockwell Hardness	Scale M	Scale M	73-76	Scale M	73-76
Polymerized density	ASTM D792	g/cm ³	1.18-1.19		
Ash content Vblack	USP281	%	0.21-0.22	%	0.21-0.22

Polypropylene-like Materials

Objet DurusWhite FullCure430

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-638-03	MPa	20-30	psi	2900-4350
Elongation at break	D-638-05	%	40-50	%	40-50
Modulus of elasticity	D-638-04	MPa	1000-1200	psi	145,000-175,000
Flexural Strength	D-790-03	MPa	30-40	psi	4350-5800
Flexural Modulus	D-790-04	MPa	1200-1600	psi	175,000-230,000
HDT, °C @ 0.45MPa	D-648-06	°C	37-42	°F	99-108
HDT, °C @ 1.82MPa	D-648-07	°C	32-34	°F	90-93
Izod Notched Impact	D-256-06	J/m	40-50	ft lb/inch	0.749-0.937
Water Absorption	D-570-98 24hr	%	1.5-1.9	%	1.5-1.9
Tg	DMA, E ₉	°C	35-37	°F	95-99
Shore Hardness (D)	Scale D	Scale D	74-78	Scale D	74-78
Rockwell Hardness	Scale M	Scale M	no data	Scale M	no data
Polymerized density	ASTM D792	g/cm ³	1.15-1.17		
Ash content	USP281	%	0.10-0.12	%	0.1-0.12

Rubber-like Materials

Objet TangoBlackPlus FullCure980 and TangoPlus FullCure930

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-412	MPa	0.8-1.5	psi	115-220
Elongation at break	D-412	%	170-220	%	170-220
Compressive set	D-395	%	4-5	%	4-5
Shore Hardness (A)	D-2240	Scale A	26-28	Scale A	26-28
Tensile Tear resistance	D-624	Kg/cm	2-4	Lb/in	18-22
Polymerized density	ASTM D792	g/cm ³	1.12-1.13		

Objet TangoBlack FullCure970

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-412	MPa	1.8-2.4	psi	115-350
Elongation at break	D-412	%	45-55	%	45-55
Compressive set	D-395	%	0.5-1.5	%	0.5-1.5
Shore Hardness (A)	D-2240	Scale A	60-62	Scale A	60-62
Tensile Tear resistance	D-624	Kg/cm	3-5	Lb/in	18-24
Polymerized density	ASTM D792	g/cm ³	1.12-1.13		

Objet TangoGray FullCure950

	ASTM	Units	Metric	Units	Imperial
Tensile strength	D-412	MPa	3-5	psi	435-725
Elongation at break	D-412	%	45-55	%	45-55
Compressive set	D-395	%	0.5-1.5	%	0.5-1.5
Shore Hardness (A)	D-2240	Scale A	73-77	Scale A	73-77
Tensile Tear resistance	D-624	Kg/cm	8-12	Lb/in	50-60
Polymerized density	ASTM D792	g/cm ³	1.16-1.17		



All data provided herein, which is related to consumables, was collected from specific specimens and tests conditions and is provided for information only. Characteristics may vary if different specimens and test conditions are applied. Unless expressly provided in writing, no warranties are made and warranties of merchantability or fitness for a particular purpose are expressly disclaimed.